



233 LV (3 Gal Bag-Pak™ Unit)

DESCRIPTION: 233 LV is a unique two-component, higher viscosity, 100% solids liquid epoxy floor coating formulated for application between 8-20 mils in thickness. 233 LV meets all USDA/FDA guidelines for use in federally inspected facilities.

PACKAGING: This container contains 2 heavy-duty Bag-Pak™ plastic bags. The larger bag contains the Resin, the smaller bag contains the Hardener. They are packaged in this 4 gallon polypropylene plastic shipping and mixing pail with a "tamper resistant" tear strip lid, ensuring that the product has not been disturbed following its original manufacture and packaging. When combined, the contents of the Hardener and Resin bags will yield a total 3 gallons of mixed 100% solids epoxy floor coating.

COVERAGE: This product is typically applied at a rate of approximately 80 to 200 sq. ft. per gallon. As with all coatings, coverage is dependent on the texture and porosity of the sub-surface.

SURFACE PREPARATION: The substrate must be clean, dry and sound with new concrete cured for at least 30 days at 70°F. Remove dust, laitance, grease, curing compounds, waxes, foreign particles, animal fats, oils, disintegrated or soft base materials, and any previously applied potentially incompatible coatings. Create a surface profile on concrete by either shot-blasting or mechanically grinding to a minimum CSP-2 profile.

MIXING: Empty the Bag-Pak™ of Resin into the mixing vessel. If TRI-CHEM UNIVERSAL COLORANT is to be added pour up to one full full Bag-Pak™ of COLORANT into the Resin and power mix with spiral style mixing blade at low speed (300 RPM) until a homogenous color is achieved. Next, empty the Bag-Pak™ of Hardener into the Resin and power mix with spiral style mixing blade at low speed (300 RPM) for two minutes. Do not entrain air during mixing. Avoid mixing and application of 233 LV if the substrate and/or air temperature are below 60°F or above 85°F or if the humidity is higher than 75% R.H. The temperature of the substrate, the epoxy, and the air in the area of installation all play a role in cure time (i.e., warmer=faster; cooler=slower). 233 LV should be tack-free and dry before applying additional coatings. This will vary with temperature and humidity, but is normally between 2-4 hours @ 75°F and 50% R.H.

APPLICATION:

1. Pour the blended product in ribbons directly onto the prepared substrate. Evenly spread with a flat blade squeegee.
2. Following the squeegee application, to provide a uniform appearance, back-roll in the opposite direction of the squeegee with a quality 3/8" nap non-shed roller. Do not allow to puddle; work the coating out of holes and voids.

POT LIFE: At 75°F and 50% R.H., 233 LV has a useful working time of 15 minutes. Using any products beyond this time will result in variable results and therefore any mixed products beyond the pot life should be discarded. Apply all mixed material as quickly as possible.

TECHNICAL DATA AND SAFETY DATA SHEET AVAILABILITY: A Technical Data Sheet and Safety Data Sheet are available from TRI-CHEM for this product. Applicators should read and understand both documents prior to mixing and applying this product.

H120-000	CAS Number
Isophoronediamine	100-51-6
Benzyl Alcohol	2855-13-2
Aliphatic Amine Adduct	Proprietary
Aliphatic Amine Blend	Proprietary
HMIS: Health - 3, Flammability - 1, Reactivity - 0 (0 - Minimal, 4 - Severe Hazard)	

R519-000	CAS Number
Bisphenol A epoxy resin	025085-99-8
Nonylphenol	25154-52-3

1-M Solvent Naphtha, Petroleum, Light Aromatic	64742-95-6
1-Methoxy-2-propanol Acetate	108-65-6
Stoddard Solvent (Mineral Spirits)	8052-41-3
1-Methoxy-2-propanol	107-98-2
HMIS: Health: 1 Flammability: 1 Reactivity: 0 (0 - Minimal, 4 - Severe Hazard)	
EPOXY RESIN COMPOUND NOT DOT REGULATED	
REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER SAFETY AND HANDLING INFORMATION.	
For Medical Emergency Information Call 800-424-9300 CHEMTREC	
DOT Technical Name: Amines, Liquid, Corrosive, N.O.S. (Isophoronediamine)	
DOT Hazard Class: Class 8	DOT I.D. Number: UN2735
	Packing Group: III

SIGNAL WORD: Danger

Hazard-determining components of labeling: Benzyl Alcohol
 Hazard Statements
 H317 May cause an allergic skin reaction
 H304 May be fatal if swallowed and enters airways
 H314 Harmful to aquatic life with long lasting effects
 H335 May cause respiratory irritation
 H314 Causes severe skin burns and eye damage
 Precautionary Statements
 P273 Avoid Release to the Environment
 P280 Wear protective gloves/ protective clothing/eye protection/face protection.
 P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue Rinsing.
 P310 Immediately Call a POISON CENTER or doctor/physician.



KEEP OUT OF THE REACH OF CHILDREN

GENERAL ADVICE: Consult a physician. Show this safety data sheet to physician in attendance.

EYES: Hold eyelids open and flush with plenty of water for at least 20 minutes. Get Medical Attention.
SKIN: Remove product and flush with plenty of water for at least 20-30 minutes. Contact a physician if irritation develops or persists. Wash with soap and water. Remove contaminated clothing immediately, wash before next use, and discard any items too difficult to clean.
INGESTION: DO NOT INDUCE VOMITING! Call a physician or poison control center immediately. Give victim a glass of water or milk. Never give anything by mouth to an unconscious person.
INHALATION: Consult a physician. Remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen.

HANDLING: Handle in a well-ventilated workspace. Empty containers may contain explosive vapors. Flush empty containers with water to remove residual flammable liquid vapors. Ground all containers during material transfer. Avoid breathing dust, vapor or mist. Avoid contact with eyes. Avoid contact with skin or clothing.

STORAGE: Keep from freezing. Keep container closed when not in use. Keep container in a cool, well-ventilated place. Keep away from food, drink, and animal feed stuffs. Keep away from ignition sources and other incompatibilities. Store in original container or a container very similar to that of the original.

DISPOSAL METHOD: The generation of waste should be avoided or minimized wherever possible. Do not dispose of with household waste. Do not dispose of in landfill. Do not allow contact with sewers or waterways. Comply with all Federal, State and Local regulations. Incinerate in admixture with fuel equipped with a scrubber to remove nitrogen oxides and carbon monoxide. Disposal of in permitted waste management facility if incineration or landfill is not practicable.

Tri-Chem | 431 Stephenson Hwy. | Troy, MI 48083 | 800.456.6255 | tri-chem.com



233 LV (3 Gal Bag-Pak™ Unit)

DESCRIPTION: 233 LV is a unique two-component, higher viscosity, 100% solids liquid epoxy floor coating formulated for application between 8-20 mils in thickness. 233 LV meets all USDA/FDA guidelines for use in federally inspected facilities.

PACKAGING: This container contains 2 heavy-duty Bag-Pak™ plastic bags. The larger bag contains the Resin, the smaller bag contains the Hardener. They are packaged in this 4 gallon polypropylene plastic shipping and mixing pail with a "tamper resistant" tear strip lid, ensuring that the product has not been disturbed following its original manufacture and packaging. When combined, the contents of the Hardener and Resin bags will yield a total 3 gallons of mixed 100% solids epoxy floor coating.

COVERAGE: This product is typically applied at a rate of approximately 80 to 200 sq. ft. per gallon. As with all coatings, coverage is dependent on the texture and porosity of the sub-surface.

SURFACE PREPARATION: The substrate must be clean, dry and sound with new concrete cured for at least 30 days at 70°F. Remove dust, laitance, grease, curing compounds, waxes, foreign particles, animal fats, oils, disintegrated or soft base materials, and any previously applied potentially incompatible coatings. Create a surface profile on concrete by either shot-blasting or mechanically grinding to a minimum CSP-2 profile.

MIXING: Empty the Bag-Pak™ of Resin into the mixing vessel. If TRI-CHEM UNIVERSAL COLORANT is to be added pour up to one full full Bag-Pak™ of COLORANT into the Resin and power mix with spiral style mixing blade at low speed (300 RPM) until a homogenous color is achieved. Next, empty the Bag-Pak™ of Hardener into the Resin and power mix with spiral style mixing blade at low speed (300 RPM) for two minutes. Do not entrain air during mixing. Avoid mixing and application of 233 LV if the substrate and/or air temperature are below 60°F or above 85°F or if the humidity is higher than 75% R.H. The temperature of the substrate, the epoxy, and the air in the area of installation all play a role in cure time (i.e., warmer=faster; cooler=slower). 233 LV should be tack-free and dry before applying additional coatings. This will vary with temperature and humidity, but is normally between 2-4 hours @ 75°F and 50% R.H.

APPLICATION:

1. Pour the blended product in ribbons directly onto the prepared substrate. Evenly spread with a flat blade squeegee.
2. Following the squeegee application, to provide a uniform appearance, back-roll in the opposite direction of the squeegee with a quality 3/8" nap non-shed roller. Do not allow to puddle; work the coating out of holes and voids.

POT LIFE: At 75°F and 50% R.H., 233 LV has a useful working time of 15 minutes. Using any products beyond this time will result in variable results and therefore any mixed products beyond the pot life should be discarded. Apply all mixed material as quickly as possible.

TECHNICAL DATA AND SAFETY DATA SHEET AVAILABILITY: A Technical Data Sheet and Safety Data Sheet are available from TRI-CHEM for this product. Applicators should read and understand both documents prior to mixing and applying this product.

H120-000	CAS Number
Isophoronediamine	100-51-6
Benzyl Alcohol	2855-13-2
Aliphatic Amine Adduct	Proprietary
Aliphatic Amine Blend	Proprietary
HMIS: Health - 3, Flammability - 1, Reactivity - 0 (0 - Minimal, 4 - Severe Hazard)	

R519-000	CAS Number
Bisphenol A epoxy resin	025085-99-8
Nonylphenol	25154-52-3

1-M Solvent Naphtha, Petroleum, Light Aromatic	64742-95-6
1-Methoxy-2-propanol Acetate	108-65-6
Stoddard Solvent (Mineral Spirits)	8052-41-3
1-Methoxy-2-propanol	107-98-2
HMIS: Health: 1 Flammability: 1 Reactivity: 0 (0 - Minimal, 4 - Severe Hazard)	
EPOXY RESIN COMPOUND NOT DOT REGULATED	
REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER SAFETY AND HANDLING INFORMATION.	
For Medical Emergency Information Call 800-424-9300 CHEMTREC	
DOT Technical Name: Amines, Liquid, Corrosive, N.O.S. (Isophoronediamine)	
DOT Hazard Class: Class 8	DOT I.D. Number: UN2735
	Packing Group: III

SIGNAL WORD: Danger

Hazard-determining components of labeling: Benzyl Alcohol
 Hazard Statements
 H317 May cause an allergic skin reaction
 H304 May be fatal if swallowed and enters airways
 H314 Harmful to aquatic life with long lasting effects
 H335 May cause respiratory irritation
 H314 Causes severe skin burns and eye damage
 Precautionary Statements
 P273 Avoid Release to the Environment
 P280 Wear protective gloves/ protective clothing/eye protection/face protection.
 P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue Rinsing.
 P310 Immediately Call a POISON CENTER or doctor/physician.



KEEP OUT OF THE REACH OF CHILDREN

GENERAL ADVICE: Consult a physician. Show this safety data sheet to physician in attendance.

EYES: Hold eyelids open and flush with plenty of water for at least 20 minutes. Get Medical Attention.
SKIN: Remove product and flush with plenty of water for at least 20-30 minutes. Contact a physician if irritation develops or persists. Wash with soap and water. Remove contaminated clothing immediately, wash before next use, and discard any items too difficult to clean.
INGESTION: DO NOT INDUCE VOMITING! Call a physician or poison control center immediately. Give victim a glass of water or milk. Never give anything by mouth to an unconscious person.
INHALATION: Consult a physician. Remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen.

HANDLING: Handle in a well-ventilated workspace. Empty containers may contain explosive vapors. Flush empty containers with water to remove residual flammable liquid vapors. Ground all containers during material transfer. Avoid breathing dust, vapor or mist. Avoid contact with eyes. Avoid contact with skin or clothing.

STORAGE: Keep from freezing. Keep container closed when not in use. Keep container in a cool, well-ventilated place. Keep away from food, drink, and animal feed stuffs. Keep away from ignition sources and other incompatibilities. Store in original container or a container very similar to that of the original.

DISPOSAL METHOD: The generation of waste should be avoided or minimized wherever possible. Do not dispose of with household waste. Do not dispose of in landfill. Do not allow contact with sewers or waterways. Comply with all Federal, State and Local regulations. Incinerate in admixture with fuel equipped with a scrubber to remove nitrogen oxides and carbon monoxide. Disposal of in permitted waste management facility if incineration or landfill is not practicable.

Tri-Chem | 431 Stephenson Hwy. | Troy, MI 48083 | 800.456.6255 | tri-chem.com